

AMENDMENTS TO THE SPECIFICATION

Page 2, after paragraph no. 2, insert the following:

G' The present invention further provides a solid golf ball comprising a solid core having a three-layered structure composed of an inner layer, an intermediate layer formed outside the inner layer, and an outer layer formed outside the intermediate layer, and a cover for coating the solid core, wherein:

the inner layer is designed to have a Shore D hardness which is lower than that of the intermediate layer;

the intermediate layer is designed to have a Shore D hardness of 45 to 65; and

the outer layer is designed to have a Shore D hardness which is lower than that of the intermediate layer.

Further, the solid golf ball as described has an inner layer with a Shore D hardness of 20 to 40.

Yet, further, the solid golf ball as described above has an inner layer with a diameter of 20.0 to 29.0 mm. The intermediate layer and the inner layer have a combined diameter of 35.0 to 39.5 mm, and the outer layer, inner layer, and intermediate layer have a combined diameter of 37.5 to 41.0 mm.

Even further, in the solid golf ball described above, a weight distribution in the solid core is designed so that the inner layer has a large specific gravity, and the intermediate layer and the outer layer have specific gravities which are smaller than the specific gravity of the inner layer.

AMENDMENT PURSUANT TO
THE DECISION ON APPEAL
USSN: 08/898,853

Q45980

Further, in the solid golf ball described above, the solid core is formed by using a rubber composition comprising a base material composed of natural and/or synthetic rubber.

G¹ Moreover, in the solid golf ball described above, at least one layer of the solid core is formed by using a material comprising one selected from ionomer resins and thermoplastic resins.

Moreover, in the solid golf ball as described above, the cover is formed by using an ionomer resin or a material containing it.
